

ALPHALAC SH-850

High Impact Polystyrene

LG Chem Ltd.

Product Description			
Alphalac of LG chemical is high functionality styrene resin and offers excellent properties and processibility .This product can be accepted as the replacement of general ABS resins.			
General			
Material Status	• Commercial: Active		
Availability	• Asia Pacific	• North America	• South America
Features	• Good Chemical Resistance	• Good Processability	
Uses	• Appliance Components		
Forms	• Pellets		
Processing Method	• Extrusion		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.04	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (200°C/5.0 kg)	3.5	g/10 min	ASTM D1238
Molding Shrinkage - Flow	0.40 to 0.80	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus ²	1670	MPa	ASTM D638
Tensile Strength ² (Yield)	24.5	MPa	ASTM D638
Tensile Elongation ²			ASTM D638
Yield	5.0	%	
Break	80	%	
Flexural Modulus ³	1710	MPa	ASTM D790
Flexural Strength ² (Yield)	36.8	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			ASTM D256
-30°C, 3.18 mm	49.0	J/m	
-30°C, 6.35 mm	49.0	J/m	
23°C, 3.18 mm	127	J/m	
23°C, 6.35 mm	98.1	J/m	
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	85		ASTM D785
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed, 6.35 mm	83.0	°C	
0.45 MPa, Annealed, 6.35 mm	88.0	°C	
1.8 MPa, Unannealed, 6.35 mm	78.0	°C	
1.8 MPa, Annealed, 6.35 mm	88.0	°C	
Vicat Softening Temperature			
--	99.0	°C	ASTM D1525 ⁴
--	85.0	°C	ASTM D1525 ⁵
Flammability	Nominal Value	Unit	Test Method
Flame Rating - UL			UL 94
1.59 mm	HB		
3.18 mm	HB		
Injection	Nominal Value	Unit	
Drying Temperature	70.0 to 80.0	°C	
Drying Time	1.0 to 2.0	hr	
Rear Temperature	190 to 210	°C	
Middle Temperature	205 to 220	°C	
Front Temperature	215 to 230	°C	
Nozzle Temperature	205 to 230	°C	
Processing (Melt) Temp	215 to 230	°C	
Mold Temperature	40.0 to 70.0	°C	

Dongguan Yi-Ming Plastic Chemical Co., Ltd.

如需要更多物性资料请查阅 www.kedisujiao.com

备注：以上原料物性数据由IDES发布,我公司仅提供参考！数据如有变动，请联系原料生产厂家获知。我公司不承担任何法律责任！

ALPHALAC SH-850
High Impact Polystyrene
LG Chem Ltd.

Wednesday, December 30, 2009

Injection	Nominal Value	Unit
Injection Pressure	60.0 to 100	MPa
Holding Pressure	50.0 to 80.0	MPa
Back Pressure	10.0 to 30.0	MPa
Screw Speed	50 to 100	rpm

Notes

¹ Typical properties: these are not to be construed as specifications.

² 50 mm/min

³ 15 mm/min

⁴ Loading 1 (10 N)

⁵ Loading 2 (50 N)

Dongguan Yi-Ming Plastic Chemical Co., Ltd.

如需要更多物性资料请查阅 www.kedisujiao.com

备注：以上原料物性数据由IDES发布,我公司仅提供参考！数据如有变动，请联系原料生产厂家获知。我公司不承担任何法律责任！