

Elastollan® 690 A 10N

Thermoplastic Polyurethane Elastomer (Polyester)

Elastogran GmbH

General	
Material Status	• Commercial: Active
Availability	• Europe
Agency Ratings	• FDA Unspecified Rating
Appearance	• Clear/Transparent
Forms	• Pellets

Physical	Nominal Value	Unit	Test Method
Density	1.21	g/cm ³	ISO 1183
Mechanical		Nominal Value	Test Method
Tensile Stress (Break)	50.0	MPa	ISO 527-2
Tensile Strain (Break)	550	%	ISO 527-2
Elastomers		Nominal Value	Test Method
Tensile Stress (100% Strain)	7.00	MPa	ISO 37
Tear Strength	90	kN/m	ISO 34-1
Hardness		Nominal Value	Test Method
Shore Hardness (Shore A)	92		ISO 868

Additional Information

Note: These properties were tested in accordance with the DIN test standard.
Stress at 20% elongation, DIN 53504: 4 Mpa
Abrasion Loss, DIN 53516: 35 mm³

Notes

¹ Typical properties: these are not to be construed as specifications.

Dongguan Yi-Ming Plastic Chemical Co., Ltd.

如需要更多物性资料请查阅 www.kedisujiao.com

备注：以上原料物性数据由IDES发布,我公司仅提供参考！数据如有变动，请联系原料生产厂家获知。我公司不承担任何法律责任！