

Elastollan® 890 A 10N

Thermoplastic Polyurethane Elastomer (Polyester)

Elastogran GmbH

General			
Material Status			• Commercial: Active
Availability			• Europe
Appearance			• Clear/Transparent
Forms			• Pellets

Physical		Nominal Value	Unit	Test Method
Density		1.22	g/cm ³	ISO 1183

Mechanical		Nominal Value	Unit	Test Method
Tensile Stress (Break)		50.0	MPa	ISO 527-2
Tensile Strain (Break)		550	%	ISO 527-2

Elastomers		Nominal Value	Unit	Test Method
Tear Strength		120	kN/m	ISO 34-1

Hardness		Nominal Value	Unit	Test Method
Shore Hardness (Shore A)		94		ISO 868

Additional Information			
Note: These properties were tested in accordance with the DIN test standard.			
Abrasion Loss, DIN 53516: 45 mm ³			

Notes

¹ Typical properties: these are not to be construed as specifications.

Dongguan Yi-Ming Plastic Chemical Co., Ltd.

如需要更多物性资料请查阅 www.kedisujiao.com

备注：以上原料物性数据由IDES发布,我公司仅提供参考！数据如有变动，请联系原料生产厂家获知。我公司不承担任何法律责任！