

Ultradur® B 4300 G6 HR Unc

Polybutylene Terephthalate

BASF Corporation

Product Description

Ultradur B 4300 G6 HR Unc. is a hydrolysis resistant, 30% fiberglass reinforced PBT, exhibiting good balance of properties and flow.

Ultradur B 4300 G6 HR Unc. was developed for automotive connectors designed to meet USCAR Class III requirements.

General

Material Status	• Commercial: Active
Availability	• Europe • North America
Filler / Reinforcement	• Glass Fiber Reinforcement, 30% Filler by Weight
Features	• Good Flow • Hydrolysis Resistant
Uses	• Automotive Applications • Connectors
Agency Ratings	• USCAR III
RoHS Compliance	• RoHS Compliant
Forms	• Pellets
Processing Method	• Injection Molding

Physical	Nominal Value	Unit	Test Method
Density	1.52	g/cm ³	ISO 1183
Viscosity Number	105	cm ³ /g	ISO 1628

Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Break, 23°C)	129	MPa	ISO 527-2
Tensile Strain (Break, 23°C)	3.7	%	ISO 527-2
Flexural Modulus (23°C)	7800	MPa	ISO 178
Flexural Strength (23°C)	199	MPa	ISO 178

Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	14	kJ/m ²	ISO 179
Charpy Unnotched Impact Strength (23°C)	78	kJ/m ²	ISO 179

Thermal	Nominal Value	Unit	Test Method
Melting Temperature (DSC)	223	°C	ISO 3146

Injection	Nominal Value	Unit
Drying Temperature	100 to 120	°C
Drying Time	4.0	hr
Suggested Max Moisture	0.040	%
Processing (Melt) Temp	250 to 275	°C
Mold Temperature	40.0 to 70.0	°C
Injection Pressure	3.50 to 12.5	MPa
Injection Rate	Fast	

Notes

¹ Typical properties: these are not to be construed as specifications.

Dongguan Yi-Ming Plastic Chemical Co., Ltd.

如需要更多物性资料请查阅 www.kedisujiao.com

备注：以上原料物性数据由厂家发布,我公司仅提供参考！数据如有变动，请联系原料生产厂家获知。我公司不承担任何法律责任！