

Ultramid® B 3GM35 Q643 (Cond)

Polyamide 6

BASF Corporation

Product Description

Ultramid B3GM35 Q643 is a 40% combined glass-fiber and mineral reinforced injection molding PA6 grade.

General

Material Status	• Commercial: Active		
Availability	• North America		
Filler / Reinforcement	• Glass Fiber Reinforcement, 15% Filler by Weight	• Mineral Filler, 25% Filler by Weight	
Additive	• Heat Stabilizer		
Features	• Good Abrasion Resistance • Good Chemical Resistance • Good Dimensional Stability • Good Flow • Good Processability	• Good Stiffness • Good Thermal Aging Resistance • Heat Stabilized • Low Viscosity • Medium Rigidity	• Oil Resistant • Paintable • Semi Crystalline
Uses	• Automotive Applications	• Handles	• Industrial Applications
RoHS Compliance	• RoHS Compliant		
Appearance	• Natural Color		
Forms	• Pellets		
Processing Method	• Injection Molding		

Impact

	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	134	J/m	ASTM D256

Notes

¹ Typical properties: these are not to be construed as specifications.

Dongguan Yi-Ming Plastic Chemical Co., Ltd.

如需要更多物性资料请查阅 www.kedisujiao.com

备注：以上原料物性数据由厂家发布,我公司仅提供参考！数据如有变动，请联系原料生产厂家获知。我公司不承担任何法律责任！